

Technical Data and Specification Sheet - Lutyens Brick

Product	Product Code	Dimensional Illustration	Length (mm)	Width (mm)	Height (mm)	Average Weight / unit (kg)	Combustibility test AS1530.1	Units per m ²	Pack Size (Blocks per pallet)	Characteristic Unconfined Compressive strength (f _{uc}) (MPa)	Durability Class	Lateral Modulus of Rupture (MPa)	eFactor (mm/m)
Lutyens Brick	LUT600.STD		590	110	65	6.5	Non-combustible	22.2	110	11	Exposure grade	1.5	<0
Lutyens Brick	LUT300.STD		290	110	65	3.2	Non-combustible	44.4	220	11	Exposure grade	1.5	<0
Lutyens Brick	LUT240.STD		230	110	65	2.5	Non-combustible	55.6	275	11	Exposure grade	1.5	<0
Lutyens Brick	LUT120.STD		110	110	65	1.2	Non-combustible	111.1	500	11	Exposure grade	1.5	<0
Lutyens Brick	LUT400.CNR		390 / 390	110	65	7.4	Non-combustible	16.7	72	11	Exposure grade	1.5	<0